



## MR.BUILD GOLD MULTIFOAM (B2) (FIRE RESISTANT)

### Product Description:

MR.BUILD GOLD FIRE RESISTANT MULTIFOAM (B2) is a single component, moisture-curing and self-expanding aerosol polyurethane foam sealant. It meets the extremely stringent requirements of DIN 4102 Pat 1 for construction material: class B2. Once cured, the foam can be cut, sawn or plastered over after only one hour providing the working temperatures (can and surfaces) are between +5 to +30°C, ideally 20°C. It is designed for easy dispensing through the straw gun included with each can. It has a fire rating of up to 240 minutes in certain configurations. (Tested according to BS 476 part 22)

### Key Performance Properties:

- 300% - Triple Expanding Foam. • Nonflammable propellant • Excellent adhesion & filling capacity
- Excellent mounting capacity and stability.
- Adheres to almost all building materials with the exception of surfaces such as polyethylene, Teflon, silicone and surface contaminated with oils and greases, mold release agents and similar materials.
- Does not contain CFC's and H-CFC's • Mold proof, water proof, over paintable.
- High thermal and acoustical insulation value • Quick drying, moisture curing
- Closed cell structure, resistant to water absorption
- Cured foam dries rigid and can be trimmed, shaped and sanded.
- Suitable for sealing high volume low moment gaps.

### Applications:

- Installation of fire protection doors and windows.
- Filling of vents and joints in fire protection constructions and sections.
- Fixing and insulation of door and window frames.
- Filling and sealing gaps, joints and cavities.
- Filling of penetrations in walls.
- Insulating electrical outlets and water pipes.
- Multi-Purpose, adhesion and fixation.

### Typical Properties:

Curing system	--	Moisture cure
Tack Free time	Minutes	15 Max.
Cutting Time	Minutes	40-50
Complete curing	Hours	24
Foam color	--	Pink

Density	Kg/m <sup>3</sup>	15-25
Adhesion Strength	kPa	PVC to PVC 143, Aluminium plates 133, Concrete to Wood 102
Elongation at break	%	8-20
Shear Strength	kPa	50-22
Compression strength	KPa	35-100 at 10% compression
Water absorption	%	Max. 0.05 volume
Thermal conductivity	35 °C W/(m.K)	<0.030
Building Material Class	--	B2 DIN 4102 part 1/ BS EN 13501-1:2007
Fire Rating	---	Up to 240 min.
Yield	Liters	35-45
Can temperature	°C	Min.-5, Max.+35
Application temperature	°C	+5 to +35
Temperature Resistance	°C	-40 to +90 when cured

### Instructions:

Optimal can temperature is +20 °C. Application (ambient) temperature is between +5 °C to +30 °C. Shake the can well before use. Screw the tube on the valve. Moisturizing the surfaces and the foam improves adhesion and shortens curing time. Hold the can upside down and activate the foam by pressing the valve. When spray please pay attention to the speed. Fill vertical joints from the bottom up when half-filled enough. When fill gaps in ceiling, uncured foam may drop because of gravity, Fresh foam can be cleaned by acetone immediately. Please support properly after filling until foam cure and adhere to the gap. Foam is tack free after about 10 minutes, can be cut after 60 minutes. Use a knife to smooth the cured foam and treated surface with cement, paint or silicone.

### Restrictions:

- Storage above +30 °C and below -5 °C shortens shelf life.
- Should be stored and transported in vertical position.
- Should be kept in room temperature for at least 12 hours before the application.
- Cured foam will discolor if exposed to ultraviolet light.
- Paint or coat the cured foam for best results in outdoor applications.
- Working at lower temperatures would decrease foam yield and cause longer curing time.

### Storage and Shelf Life:

12 months when stored at 20°C / 50% relative humidity out of direct sunlight.

### Packaging:

MR.BUILD GOLD MULTIFOAM B2 (Straw Type & Gun Type) 750 ML - 12 CANS/CTN

**Safety:**

Contains Diphenylmethane-4,4'-Diisocyanate. Harmful by inhalation. Irritating to eyes, respiratory system and skin. Do not breathe spray/vapour. Wear suitable protective clothing and gloves. Use only in well-ventilated areas. Pressurized container. Keep away from direct sunlight and do not expose temperatures over 50 °C. Do not pierce or burn, even after use. Keep away from sources of ignition, no smoking. Keep out of the reach of child.

**Shipping Limitations: None****Note:** \_\_\_\_\_

The information and data contained in the product data sheet is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of the product for usage. Since the supplier cannot know all the uses, or the conditions of use to which the product may be exposed, no warranties concerning the fitness or suitability for particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application Likewise if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Integra Firestoppers LLP****HEAD OFFICE**

Gate No.2, Plot No. 60A, Kandivali Industrial Area,  
Charkop,Kandivali (W), Mumbai 400067  
Call: +91 90046 76151 Email us - sales@integrapro.in

**NORTHERN REGION OFFICE**

Noida One - IT Park, Tower B, 5th Floor,  
Plot No - B-8, Sector-62, Noida, India - 201309  
Call: +91 90046 76154 Email us - sales@integrapro.in